



**CATIONIC RAPID SETTING EMULSIFIED ASPHALT
CRS-2**

CRS-2 is a cationic rapid setting emulsified asphalt meeting the specifications of AASHTO M208 and ASTM D2397.

The emulsified asphalt shall conform to the following requirements:

<u>PROPERTY</u>	<u>CRS-2</u>	<u>ASTM TEST</u>
TEST ON EMULSION:		
Viscosity, Saybolt Furol at 122°F, sec/	100-400	D88
Storage stability test, 24 hours, %	1 maximum	D244
Classification test	passes	
Particle charge test	positive	D244
Sieve test, %	0.1 maximum	D244
Oil distillate, by volume, %	3 maximum	D244
Residue, %	65 minimum	D244
TEST ON RESIDUE:		
Penetration, 77°F, 100g, 5 sec.	100-250	D5
Ductility, 77°F, 5cm/min, cm.	40 minimum	D113
Solubility in trichloroethylene, %	97.5 minimum	D2042